

Nordic Lam™
Nordic Structures

PR-L294(C)
Revised December 21, 2023

Products: Nordic Lam™

Nordic Structures, 1100 Avenue des Canadiens-de-Montréal, Suite 100, Montreal, Québec
H3B 2S2, Canada
(514) 871-8526
www.nordic.ca

1. Basis of the product report:
 - 2020 National Building Code of Canada (NBC): Clause 1.2.1.1 of Division A and Clauses 4.1, 4.3.1, 9.23.4.2, and 9.23.10.1 of Division B
 - CSA O86-19 Engineering Design in Wood
 - CSA O122-16 Structural Glued Laminated Timber recognized in CSA O86-19
 - CSA O177-06 (R2015) Qualification Code for Manufacturers of Structural Glued-Laminated Timber recognized in CSA O86-19
 - APA Reports T2001P-85, T2003P-21, T2004P-43, T2005P-74, T2006P-45, T2008P-91, T2009P-39, and T2012P-41, FPInnovations Reports 201003404, 201003409, 201005209, 301008842, 301009694, and 301011496, and other qualification data
2. Product description:

Nordic Lam™ is structural glued laminated timber (glulam) manufactured with Spruce-Pine-Fir (mainly Black Spruce) lumber in accordance with layup combinations developed in accordance with the principle of ASTM D3737, ASTM D7341 and full-scale tests. The end joints within the Nordic Lam are randomly spaced within the same lamination and are not required to be spaced a minimum of 1.8 m (71 inches) apart. Nordic Lam is used as beams, headers, rafters, purlins, columns, studs, and decking, and is manufactured in nominal widths ranging from 38 to 686 mm (1-1/2 to 27 inches), a variety of depths, and lengths up to 24.4 meters (80 feet), in accordance with Table 1.
3. Design properties:

Table 2 lists the engineering properties for Nordic Lam beams. The maximum design loads for Nordic Lam beams shall be in accordance with the recommendations provided by the manufacturer (www.nordic.ca/en/documentation/technical-documents/ns-gt5-ca).

Table 3 lists the engineering properties for Nordic Lam columns. The maximum design loads for Nordic Lam columns shall be in accordance with the recommendations provided by the manufacturer (www.nordic.ca/en/documentation/technical-documents/ns-gt5-ca).
4. Product installation:

Nordic Lam beams and columns shall be installed in accordance with the recommendations provided by the manufacturer (www.nordic.ca/en/documentation/technical-documents/ns-gt5-ca) and APA Construction Guide: *Glulam Connection Details*, Form T300 (www.apawood.org/resource-library). Permissible field notching and drilling of Nordic Lam beams shall be in accordance with the recommendations provided by the manufacturer and APA Technical Notes: *Field Notching and Drilling of Glued Laminated Timber Beams*, Form S560, and *Effect of Large Diameter Horizontal Holes on the Bending and Shear Properties of Structural Glued Laminated Timber*, Form V700 (see link above). Permissible field notching and drilling of Nordic Lam columns shall be in accordance with the recommendations provided by the manufacturer.

5. Fire-rated assemblies:

Fire-rated assemblies shall be constructed in accordance with the recommendations provided by the manufacturer (see link above). Procedures specified in Annex B of the 2019 CSA O86 may be considered in designing glulams exposed to fire up to 2 hours when permitted by the authority having jurisdiction. The fire-resistance rating shall be evaluated in accordance with Appendix D-2.11 of the 2020 NBC.

Nordic Lam has been tested in accordance with CAN/ULC S102 and meets the flame-spread rating of 26 – 75 and smoke developed classification of 0 – 450.

6. Limitations:

- a) Nordic Lam beams and columns shall be designed in accordance with the code using the engineering properties specified in this report.
- b) The dimensions of Nordic Lam beams and columns shall follow those specified in Table 1.
- c) Nordic Lam beams and columns shall be manufactured in accordance with layup combinations specified in ANSI 117, *Standard Specification for Structural Glued Laminated Timber of Softwood Species*, or proprietary Nordic Lam manufacturing specifications documented in the in-plant manufacturing standard approved by APA.
- d) Nordic Lam is produced at the Nordic Structures, Chibougamau, Quebec facilities under a quality assurance program audited by APA.
- e) This report is subject to re-examination in one year.

7. Identification:

Nordic Lam described in this report is identified by a label bearing the manufacturer's name (Nordic Structures) and/or trademark, the APA assigned plant number (1057), the APA logo, the combination symbol, the report number PR-L294 or PR-L294C, and a means of identifying the date of manufacture.

Table 1. Dimensions for Nordic Lam layups

| Layup | Minimum width, b (mm) | Maximum width, b (mm) | Minimum depth | Maximum depth, h (mm) |
|-------------|-----------------------|-----------------------|---------------|-----------------------|
| 20F-E8M1 | 38 | 191 | 4 lams | 457 |
| 20F-ES/CPG | 79 ⁽¹⁾ | 89 | 4 lams | 457 |
| 24F-E/ES1M1 | 38 | 191 | 4 lams | 914 ⁽²⁾ |
| 24F-ES/MSR | 79 | 89 | 4 lams | 914 ⁽²⁾ |
| 24F-ES/NPG | 38 | 686 | 4 lams | NA ⁽²⁾ |
| ES11 | 38 | 191 | 2 lams | 381 |
| ES11/NPG | 38 | 191 | 2 lams | 381 |
| ES12 | 38 | 191 | 2 lams | 381 |
| ES12/NPG | 38 | 686 | 2 lams | 1,372 ⁽²⁾ |

⁽¹⁾ The minimum width shall be permitted to be 38 mm when 24F-ES/NPG is trademarked as 20F-ES/CPG.

⁽²⁾ The maximum depth shall not exceed the tabulated depth or a depth-to-width ratio of 12:1, whichever is smaller.

Table 2. Specified Strengths (MPa) and Relative Density for Nordic Lam Beams^(1,2,3)

| Stress grade | 20F-1.9E | 20F-1.6E | 24F-1.9E | 24F-1.9E | 24F-1.9E | Wet-Use Factor |
|---|------------|----------|--------------------|--------------------|--------------------|----------------|
| EWS combination layup symbol ⁽⁹⁾ | 20F-ES/CPG | 20F-E8M1 | 24F-E/ES1M1 | 24F-ES/NPG | 24F-ES/MSR | |
| Bending about X-X Axis (Loaded Perpendicular to Wide Faces of Laminations) | | | | | | |
| Bending at extreme fibre due to positive bending moment (F_{bx}^{+}) ⁽⁷⁾ | 25.6 | 25.6 | 30.7 | 30.7 | 30.7 | 0.80 |
| Bending at extreme fibre due to negative bending moment (F_{bx}^{-}) ⁽⁷⁾ | 25.6 | 25.6 | 30.7 | 30.7 | 30.7 | 0.80 |
| Longitudinal shear (F_{vx}) ^(4,8) | 2.2 | 2.2 | 2.2 | 2.5 | 2.2 | 0.87 |
| Compression perpendicular to grain (F_{cpX}) ⁽¹⁰⁾ | | | | | | |
| Compression face | 5.8 | 5.8 | 7.5 ⁽⁶⁾ | 7.5 ⁽⁶⁾ | 7.5 ⁽⁶⁾ | 0.67 |
| Tension face | 5.8 | 5.8 | 7.5 ⁽⁶⁾ | 7.5 ⁽⁶⁾ | 7.5 ⁽⁶⁾ | 0.67 |
| True Modulus of Elasticity (E_x) | 13,100 | 11,000 | 13,100 | 13,100 | 13,100 | 0.90 |
| Apparent Modulus of Elasticity ($E_{x,app}$) ⁽⁵⁾ | 12,400 | 10,300 | 12,400 | 12,400 | 12,400 | 0.90 |
| Bending about Y-Y Axis (Loaded Parallel to Wide Faces of Laminations) | | | | | | |
| Bending at extreme fibre due to Positive Bending Moment (F_{by}^{+}) ⁽⁷⁾ | 25.6 | 13.4 | 14.1 | 30.7 | 14.1 | 0.80 |
| Bending at extreme fibre due to Negative Bending Moment (F_{by}^{-}) ⁽⁷⁾ | 25.6 | 13.4 | 14.1 | 30.7 | 14.1 | 0.80 |
| Longitudinal shear (F_{vy}) ⁽⁴⁾ | 2.2 | 1.5 | 1.5 | 2.5 | 1.5 | 0.87 |
| Compression perpendicular to grain (F_{cpy}) | | | | | | |
| Compression face | 5.8 | 3.9 | 3.8 | 7.5 ⁽⁶⁾ | 3.8 | 0.67 |
| Tension face | 5.8 | 3.9 | 3.8 | 7.5 ⁽⁶⁾ | 3.8 | 0.67 |
| True Modulus of Elasticity (E_y) | 13,100 | 10,300 | 11,000 | 13,100 | 11,000 | 0.90 |
| Apparent Modulus of Elasticity ($E_{y,app}$) ⁽⁵⁾ | 12,400 | 9,700 | 10,300 | 12,400 | 10,300 | 0.90 |
| Axially Loaded | | | | | | |
| Compression parallel to grain (F_c) | 14.4 | 14.4 | 16.5 | 33.0 | 16.5 | 0.75 |
| Tension parallel to grain (F_t) | 10.2 | 10.2 | 13.4 | 20.4 | 13.4 | 0.75 |
| Tension perpendicular to grain (F_{tp}) | 0.51 | 0.51 | 0.51 | 0.51 | 0.51 | 0.85 |
| Modulus of elasticity (E_{axial}) | 13,100 | 9,700 | 11,000 | 13,100 | 11,000 | 0.90 |
| Connections Design | | | | | | |
| Mean oven-dry relative density (G) | 0.42 | 0.42 | 0.42 | 0.47 | 0.42 | – |

(1) The combinations in this table are applicable to members consisting of 4 or more laminations, unless otherwise noted.
 (2) Design of glulam members shall be in accordance with CSA O86, Engineering Design in Wood (Limit States Design).
 (3) The tabulated design values are for standard-term load duration and dry conditions of use. For other load durations, see applicable design code. For wet conditions of use, multiply the tabulated values by the wet-use factors shown in the rightmost column of the table.
 (4) Specified longitudinal shear has been adjusted to a 2.0 m³ of beam volume.
 (5) The tabulated apparent E values have already included a 5% shear deflection.
 (6) The F_{cp} value is applicable to glulam members made with manufactured lumber. Otherwise, the F_{cp} value shall be 7.0 MPa.
 (7) In calculating the size factor for bending, K_{zb} , the beam width, b, must be taken as the full member width (mm).
 (8) In calculating the factored fracture shear resistance at a notch on the tension side at a support, F_r , the effective lamination width, b_{eff} , must be taken as the beam width (mm).
 (9) ES = Eastern spruce.
 (10) In calculating the size factor for bearing, K_{zbp} , the beam width, b, must be taken as the full member width (mm).

Table 3. Specified Strengths (MPa) and Relative Density for Nordic Lam Columns^(1,2,3)

| Stress grade | ES11 | ES11 | ES12 | ES12 | Wet-Use Factor |
|---|--|--|--|--|----------------|
| EWS combination layup symbol ⁽⁸⁾ | EWS ES11 | ES11/NPG | EWS ES12 | ES12/NPG | |
| Bending about X-X Axis (Loaded Perpendicular to Wide Faces of Laminations) | | | | | |
| Bending at extreme fibre due to positive bending moment (F_{bx}^{+}) ⁽⁹⁾ | 17.2 ⁽⁶⁾ | 17.2 | 24.9 ⁽⁶⁾ | 30.7 | 0.80 |
| Bending at extreme fibre due to negative bending moment (F_{bx}^{-}) ⁽⁹⁾ | 17.2 ⁽⁶⁾ | 17.2 | 24.9 ⁽⁶⁾ | 30.7 | 0.80 |
| Longitudinal shear (F_{vx}) ^(4,10) | 2.2 | 2.2 | 2.2 | 2.5 | 0.87 |
| Compression perpendicular to grain (F_{cp}) ⁽¹¹⁾ | | | | | |
| Compression face | 5.8 | 5.8 | 7.5 ⁽⁷⁾ | 7.5 ⁽⁷⁾ | 0.67 |
| Tension face | 5.8 | 5.8 | 7.5 ⁽⁷⁾ | 7.5 ⁽⁷⁾ | 0.67 |
| True Modulus of Elasticity (E_x) | 11,000 | 11,000 | 13,100 | 13,100 | 0.90 |
| Apparent Modulus of Elasticity ($E_{x,app}$) ⁽⁵⁾ | 10,300 | 10,300 | 12,400 | 12,400 | 0.90 |
| Bending about Y-Y Axis (Loaded Parallel to Wide Faces of Laminations) | | | | | |
| Bending at extreme fibre due to Positive Bending Moment (F_{by}^{+}) | 22.4 (4+ lams) 20.4 (3 lams) 17.9 (2 lams) | 22.4 (4+ lams) 20.4 (3 lams) 17.9 (2 lams) | 30.7 (4+ lams) 30.7 (3 lams) 29.4 (2 lams) | 30.7 (4+ lams) 30.7 (3 lams) 29.4 (2 lams) | 0.80 |
| Bending at extreme fibre due to Negative Bending Moment (F_{by}^{-}) | 22.4 (4+ lams) 20.4 (3 lams) 17.9 (2 lams) | 22.4 (4+ lams) 20.4 (3 lams) 17.9 (2 lams) | 30.7 (4+ lams) 30.7 (3 lams) 29.4 (2 lams) | 30.7 (4+ lams) 30.7 (3 lams) 29.4 (2 lams) | 0.80 |
| Longitudinal shear (F_{vy}) ⁽⁴⁾ | 1.5 | 1.5 | 1.5 | 2.5 | 0.87 |
| Compression perpendicular to grain (F_{cpy}) | | | | | |
| Compression face | 5.8 | 5.8 | 7.5 ⁽⁷⁾ | 7.5 ⁽⁷⁾ | 0.67 |
| Tension face | 5.8 | 5.8 | 7.5 ⁽⁷⁾ | 7.5 ⁽⁷⁾ | 0.67 |
| True Modulus of Elasticity (E_y) | 11,000 | 11,000 | 13,100 | 13,100 | 0.90 |
| Apparent Modulus of Elasticity ($E_{y,app}$) ⁽⁵⁾ | 10,300 | 10,300 | 12,400 | 12,400 | 0.90 |
| Axially loaded | | | | | |
| Compression parallel to grain (F_c) | 22.3 (4+ lams) 19.4 (2-3 lams) | 22.3 (4+ lams) 19.4 (2-3 lams) | 33.0 (4+ lams) 24.4 (2-3 lams) | 33.0 (4+ lams) 24.4 (2-3 lams) | 0.75 |
| Tension parallel to grain (F_t) | 12.5 | 12.5 | 20.4 | 20.4 | 0.75 |
| Tension perpendicular to grain (F_{tp}) | 0.51 | 0.51 | 0.51 | 0.51 | 0.85 |
| Modulus of elasticity (E_{axial}) | 11,000 | 11,000 | 13,100 | 13,100 | 0.90 |
| Connections Design | | | | | |
| Mean oven-dry relative density (G) | 0.42 | 0.42 | 0.42 | 0.47 | – |

(1) The combinations in this table are applicable to members consisting of 4 or more laminations, unless otherwise noted.
 (2) Design of glulam members shall be in accordance with CSA O86, Engineering Design in Wood (Limit States Design).
 (3) The tabulated design values are for standard-term load duration and dry conditions of use. For other load durations, see applicable design code. For wet conditions of use, multiply the tabulated values by the wet-use factors shown in the rightmost column of the table.
 (4) Specified longitudinal shear has been adjusted to a 2.0 m³ of beam volume.
 (5) The tabulated apparent E values have already included a 5% shear deflection.
 (6) When the member depth is greater than 381 mm (15 inches), the tabulated F_{bx} values shall be multiplied by a factor of 0.88.
 (7) The F_{cp} value is applicable to glulam members made with manufactured lumber. Otherwise, the F_{cp} value shall be 7.0 MPa.
 (8) ES = Eastern spruce.
 (9) In calculating the size factor for bending, K_{zb} , the beam width, b, must be taken as the full member width (mm).
 (10) In calculating the factored fracture shear resistance at a notch on the tension side at a support, F_r , the effective lamination width, b_{eff} , must be taken as the beam width (mm).
 (11) In calculating the size factor for bearing, K_{zcp} , the beam width, b, must be taken as the full member width (mm).

APA – The Engineered Wood Association is an approved national standards developer accredited by American National Standards Institute (ANSI). APA publishes ANSI standards and Voluntary Product Standards for wood structural panels and engineered wood products. APA is an accredited certification body under ISO/IEC 17065 by Standards Council of Canada (SCC), an accredited inspection agency under ISO/IEC 17020 by International Code Council (ICC) International Accreditation Service (IAS), and an accredited testing organization under ISO/IEC 17025 by IAS. APA is also an approved Product Certification Agency, Testing Laboratory, Quality Assurance Entity, Validation Entity, and Product Evaluation Entity by the State of Florida, and an approved testing laboratory by City of Los Angeles.

**APA – THE ENGINEERED WOOD ASSOCIATION
HEADQUARTERS**

7011 So. 19th St. ▪ Tacoma, Washington 98466
Phone: (253) 565-6600 ▪ Fax: (253) 565-7265 ▪ Internet Address: www.apawood.org

PRODUCT SUPPORT HELP DESK
(253) 620-7400 ▪ *E-mail Address:* help@apawood.org

DISCLAIMER

APA Product Report® is a trademark of *APA – The Engineered Wood Association*, Tacoma, Washington. The information contained herein is based on the product evaluation in accordance with the references noted in this report. Neither APA, nor its members make any warranty, expressed or implied, or assume any legal liability or responsibility for the use, application of, and/or reference to opinions, findings, conclusions, or recommendations included in this report. Consult your local jurisdiction or design professional to assure compliance with code, construction, and performance requirements. Because APA has no control over quality of workmanship or the conditions under which engineered wood products are used, it cannot accept responsibility for product performance or designs as actually constructed.