

ICC-ES Evaluation Report

ESR-2909

Reissued September 2023

This report also contains:

-CBC Supplement


Subject to renewal September 2025

-FBC Supplement

-LABC Supplement

ICC-ES Evaluation Reports are not to be construed as representing aesthetics or any other attributes not specifically addressed, nor are they to be construed as an endorsement of the subject of the report or a recommendation for its use. There is no warranty by ICC Evaluation Service, LLC, express or implied, as to any finding or other matter in this report, or as to any product covered by the report.

Copyright © 2023 ICC Evaluation Service, LLC. All rights reserved.

<p>DIVISION: 06 00 00 - WOOD, PLASTICS, AND COMPOSITES</p> <p>Section: Section: 06 17 13—Laminated Veneer Lumber</p>	<p>REPORT HOLDER: PACIFIC WOODTECH CORPORATION</p>	<p>EVALUATION SUBJECT: PACIFIC WOODTECH® LAMINATED VENEER LUMBER (LVL), PACIFIC WOODTECH® TREATED LVL AND PACIFIC WOODTECH® RIM BOARDS</p>	
--	---	---	---

1.0 EVALUATION SCOPE

Compliance with the following codes:

- 2021, 2018, 2015, 2012 and 2009 [International Building Code® \(IBC\)](#)
- 2021, 2018, 2015, 2012 and 2009 [International Residential Code® \(IRC\)](#)

For evaluation for compliance with codes adopted by the Los Angeles Department of Building and Safety (LADBS), see [ESR-2909 LABC and LARC Supplement](#).

Properties evaluated:

- Structural
- Fireblocking

2.0 USES

Pacific Woodtech laminated veneer lumber (LVL) and Pacific Woodtech Treated LVL are used in structural applications such as beams, headers, joists, rafters, columns, and truss chords. Pacific Woodtech Rim Boards are used in rim board applications as described in this report.

3.0 DESCRIPTION

Pacific Woodtech LVL and Pacific Woodtech Rim Boards are structural composite lumber products complying with ASTM D5456 and additional performance requirements specified in the ICC-ES Acceptance Criteria for Structural Wood-based Products (AC47) and the Acceptance Criteria for Rim Board Products (AC124). Qualified adhesives, veneer species and veneer grades are as specified in the approved quality control manual. The veneers are laminated with the grain parallel to the length of the LVL member. Pacific Woodtech LVL is available in thicknesses from $\frac{3}{4}$ inch (19.1 mm) to 7 inches (178 mm) and depths from $1\frac{3}{4}$ inches (44.5 mm) to 48 inches (1219 mm). Products thicker than $3\frac{1}{2}$ inches (89 mm) are fabricated by means of a secondary face-bonding process. Pacific Woodtech Rim Boards are manufactured from Pacific Woodtech LVL in thicknesses of $1\frac{1}{4}$, $1\frac{1}{2}$ and $1\frac{3}{4}$ inches (32 mm, 38 mm and 44 mm), a maximum depth of 24 inches (610 mm), and a minimum length of 8 feet (2438 mm).

Pacific Woodtech Treated LVL is fabricated with Propiconazole Tebuconazole Imidacloprid (PTI) as part of the in-glueline treatment during the LVL manufacturing process for fungal decay and resistance to wood

destroying insects, including Formosan termites, to a retention level equivalent to that specified in ICC-ES Evaluation Report ESR-3834 for the Use Categories UC1 through UC4A. Pacific Woodtech Treated LVL shall be limited to the above ground applications including, but not limited to, structural members that are hard to maintain, repair or replace and are critical to the performance and safety of the structure system.

4.0 DESIGN AND INSTALLATION

4.1 Design:

4.1.1 General: The design provisions for structural composite lumber in the ANSI/AWC *National Design Specification*[®] (NDS) for Wood Construction, as referenced in the applicable code, are applicable to Pacific Woodtech LVL, unless otherwise noted in this report. Reference design values for Pacific Woodtech LVL and Pacific Woodtech Treated LVL are provided in [Tables 1A](#) and [1B](#).

4.1.2 Connections: Reference lateral and withdrawal design values for nailed or bolted connections in Pacific Woodtech LVL and Pacific Woodtech Treated LVL are as specified in the NDS for structural composite lumber having equivalent specific gravities as given in [Table 3](#) of this report. For fasteners installed perpendicular to the wide face of the veneers, spacing, edge distances and end distances must be as required in the NDS for sawn lumber. Minimum required spacing, edge distances and end distances for fasteners installed into the narrow face of the LVL (faces showing the narrow edge of all veneers) are as given in [Table 4](#). Bolted connections are not allowed in member edges.

Connections, other than the nailed and bolted connections described herein, are outside the scope of this report.

Exception: Lag screw connections between Pacific Woodtech Rim Boards and deck ledgers have an allowable lateral load of 350 pounds (1.56 kN) per lag screw, under the following conditions:

- Lag screws must have a minimum nominal diameter of $\frac{1}{2}$ inch (12.7 mm), and sufficient length so that the full diameter of the lag screw shank penetrates through the rim board (the tapered tip must pass completely through the rim board).
- Deck ledgers must consist of minimum 2-by-8 lumber having a minimum assigned specific gravity of 0.42.
- Sheathing between the rim board and the deck ledger must consist of wood structural panels meeting PS-1 or PS-2 and be attached to the rim board in accordance with the applicable code.
- One flat washer must be used between the deck ledger and the lag screw head.
- Edge distances from the center of the lag screw to the edges of the rim board and deck ledger must be 2 inches (51 mm) or greater. End distances must be 4 inches (102 mm) or greater.
- The lag screws must be installed, and adjustment factors must be applied as applicable, in accordance with the NDS.
- Rim boards and deck ledgers must be checked for load-carrying capacity at connections in accordance with Section 11.1.2 of the NDS.

4.1.3 Rim Boards: Allowable loads for Pacific Woodtech Rim Boards are given in [Table 2](#). Toe-nailed connections of rim boards are not limited by the 150 plf (2189 N/m) lateral load capacity noted for Seismic Design Categories D, E, and F in Section 4.1.7 of the ANSI/AWC Special Design Provisions for Wind and Seismic (SDPWS).

4.1.4 Fireblocking: Pacific Woodtech LVL may be used as fireblocking in lieu of the materials listed in Section 718.2.1 of the 2021, 2018, 2015 and 2012 IBC, Section 717.2.1 of the 2009 IBC, and Section R302.11.1 of the IRC, as applicable. LVL used as fireblocking must have a minimum thickness of $1\frac{1}{2}$ inches (38 mm), with the exception that $\frac{3}{4}$ -inch-thick (19 mm) LVL may be used, provided the joints are backed by a second layer of $\frac{3}{4}$ -inch-thick (19 mm) LVL.

4.2 Installation:

4.2.1 General: Installation of Pacific Woodtech LVL, Pacific Woodtech Treated LVL, and Pacific Woodtech[®] Rim Boards must comply with this report and with the manufacturer's published installation instructions. The manufacturer's published installation instructions must be available at the jobsite at all times during installation.

4.2.2 Rim Boards: Pacific Woodtech Rim Boards must be installed as a continuously supported structural element located at the joist elevation in an end bearing wall or parallel to the joist framing. It must be the full depth of the joist space and be used for any combination of the following: (1) transfer of vertical loads, from

above to below, at the rim board location; (2) diaphragm attachment (e.g., sheathing to top edge of rim board); (3) transfer of in-plane lateral loads from the diaphragm to the wall plate below; (4) to provide lateral support to the joist (i.e., resistance against rotation) through attachment to the joist; (5) to provide closure for ends of joists; or (6) as an attachment base for siding and/or exterior deck ledgers.

5.0 CONDITIONS OF USE

The Pacific Woodtech LVL, Pacific Woodtech Treated LVL and Pacific Woodtech Rim Boards described in this report comply with, or are suitable alternatives to what is specified in, those codes listed in Section 1.0 of this report, subject to the following conditions:

- 5.1 Design and installation must comply with this report, the manufacturer's published installation instructions, and the applicable code. In the event of a conflict between this report and the manufacturer's published installation instructions, this report governs.
- 5.2 Design calculations and/or drawings, demonstrating compliance with this report, must be provided to the code official upon request. These documents must be sealed by a registered design professional where required by the statutes of the jurisdiction in which the project is to be constructed.
- 5.3 Plank compression perpendicular to grain, $F_{c\perp}$, values in [Table 1](#) are allowed to be adjusted by the NDS specified bearing area factor, C_b .
- 5.4 With the exception for Pacific Woodtech Treated LVL, applications in unprotected, wet service conditions, where the moisture content of the LVL will reach 16 percent or greater, are beyond the scope of this report.
- 5.5 Pacific Woodtech Treated LVL may be used in exterior construction above ground applications (UC3B), including components that are difficult to maintain, repair, or replace and are critical to the performance and safety of the building structure.
- 5.6 Pacific Woodtech LVL products are produced at the Pacific Woodtech Corporation manufacturing plant located in Burlington, Washington, under a quality-control program with inspections by ICC-ES and APA—The Engineered Wood Association (AA-649).

6.0 EVIDENCE SUBMITTED

- 6.1 Data in accordance with the [ICC-ES Acceptance Criteria for Structural Wood-based Products \(AC47\)](#), dated June 2017 (Editorially revised February 2021).
- 6.2 Data in accordance with the [ICC-ES Acceptance Criteria for Rim Board Products \(AC124\)](#), dated June 2019 (Editorially revised February 2021).

7.0 IDENTIFICATION

- 7.1 Pacific Woodtech LVL and Pacific Woodtech Treated LVL are identified by a stamp noting the manufacturer's name (Pacific Woodtech), product trade name, grade, production date, evaluation report number (ESR-2909), qualified inspection agency name or logo (APA), and manufacturer's APA mill number (1047).
- 7.2 Pacific Woodtech Rim Boards are identified by a stamp noting the manufacturer's name (Pacific Woodtech), product trade name, product name or registered trademark, grade, thickness, production date, evaluation report number (ESR-2909), name of the inspection agency (APA—The Engineered Wood Association) and manufacturer's APA mill number (1047).
- 7.3 The report holder's contact information is the following:

PACIFIC WOODTECH CORPORATION
1850 PARK LANE
BURLINGTON, WASHINGTON 98233
(360) 707-2200
www.pacificwoodtech.com

TABLE 1A—PACIFIC WOODTECH[®] LVL AND TREATED LVL REFERENCE DESIGN VALUES (psi)^{1, 2}

True E		Apparent E		Beam ³			Plank ⁴			Axial	
Grade	MOE (10 ⁶ psi) ⁵	Grade	MOE (10 ⁶ psi) ⁶	F _b (psi) ⁷	F _v (psi)	F _{cL} (psi)	F _b (psi) ⁷	F _v (psi)	F _{cL} (psi) ⁸	F _t (psi) ⁹	F _c (psi)
1.6E	1.6	1.5E	1.5	2,250	230	750	2,250	150	650	1,500	1,950
1.9E	1.9	1.8E	1.8	2,750	285	850	2,750	150	650	1,850	2,450
PWT Treated	2.0	PWT Treated	1.9	2,800	285	850	2,800	150	650	2,100	2,500
2.0E	2.0	1.9E	1.9	2,900	285	750	2,950	150	650	2,100	3,200
2.1E	2.1	2.0E	2.0	2,900	285	850	2,900	150	650	2,100	3,200
2.1E	2.1	2.0E	2.0	3,100	285	850	3,100	150	650	2,100	3,200
2.3E	2.3	2.2E	2.2	3,100	285	850	3,100	150	650	2,350	3,200

For **SI**: 1 psi = 6.895 kPa, 1 inch = 25.4 mm.

¹Reference design values are based on dry conditions of use, in which the environmental conditions (temperature and relative humidity) will result in an average equilibrium moisture content (EMC) of sawn lumber of less than 16 percent. Applications where the EMC will equal or exceed 16 percent are outside the scope of this report, except for PWT Treated LVL. Design values for PWT Treated LVL when used in EMC of 16% or greater are provided in [Table 1B](#).

²Reference design values must be adjusted, as applicable, in accordance with Section 8.3 of the NDS.

³Beam values apply to members loaded and supported on faces showing the narrow edge of all veneers, typically the narrow faces of the member.

⁴Plank values apply to members loaded and supported on faces showing the wide face of one veneer, typically the wide faces of the member.

⁵Tabulated values are the true (shear-free) modulus of elasticity. Coefficient of variation of E_{true} may be taken as 0.10.

⁶Tabulated values are the apparent modulus of elasticity. The reference modulus of elasticity for beam stability and column stability calculations, E_{min} , must be calculated in accordance with Appendix D of the NDS. When calculating E_{min} , the coefficient of variation of modulus of elasticity, COV_E , may be taken as 0.10.

⁷Reference tension design values parallel to grain, F_t , apply to a 4-foot member length. For member lengths greater than 4 feet, F_t must be multiplied by a factor of $(4/L)^{0.10}$, where L is the length of the member, in feet.

⁸The volume factor, C_v , which is applicable to reference bending design values, F_b , in accordance with Section 8.3 of the NDS, must be calculated as follows: For *beam* orientation: $C_v = (12/d)^{0.20} \leq 1.47$; For *plank* orientation: $C_v = (1.75/d)^{0.33} \leq 1.00$, where d is the member depth in inches.

⁹Plank compression perpendicular to grain, F_{cL} , values are allowed to be adjusted by the NDS specified bearing area factor, C_b .

TABLE 1B—PACIFIC WOODTECH[®] TREATED LVL REFERENCE DESIGN VALUES FOR WET-USE^{1, 2}

True E		Apparent E		Beam ³			Plank ⁴			Axial	
Grade	MOE ⁵ (10 ⁶ psi)	Grade	MOE ⁶ (10 ⁶ psi)	F _b ⁷ (psi)	F _v (psi)	F _{cL} (psi)	F _b ⁷ (psi)	F _v (psi)	F _{cL} ⁸ (psi)	F _t ⁹ (psi)	F _c (psi)
PWT Treated	1.4	PWT Treated	1.3	1,680	160	465 ¹⁰	1,680	100	355 ¹⁰	1,780	875

For **SI**: 1 psi = 6.895 kPa, 1 inch = 25.4 mm.

¹Reference design values are based on wet conditions of use, in which the environmental conditions (temperature and relative humidity) will result in an average equilibrium moisture content (EMC) of sawn lumber of 16% or greater.

²Reference design values must be adjusted, as applicable, in accordance with Section 8.3 of the NDS, except for the wet service factor (C_M).

³⁻⁹See Footnotes to [Table 1A](#).

¹⁰Deformation up to 0.125 inch could occur at the tabulated compressive stress perpendicular to grain in wet-use conditions.

TABLE 2—1¹/₄, 1¹/₂, 1³/₄- INCH RIM BOARD ALLOWABLE LOADS^{1, 2, 3, 4}

True E (10 ⁶ psi)	Apparent E (10 ⁶ psi)	Minimum Thickness (in.)	Depth (in.)	Vertical Load Capacity		Lateral Load Capacity (plf)	Deck Ledger Connection ⁵ (1/2" dia. lag screw) (lbf)	Deck Ledger Connection (1/2" dia. bolt) (lbf)	Deck Ledger Connection (1/2" dia. bolt w/ air gap) (lbf)
				Uniform Load (plf)	Concentrated Load (lbf)				
1.6	1.5	1-1/4	11-7/8	4,250	3,760	200	550	550	350
			14	3,550	3,550				
			16	2,900	2,900				
		1-1/2	11-7/8	6,480	4,500	250	550	550	615
			14	5,600	4,500				
			16	4,800	4,500				
			18	3,900	2,700				
			20	3,200	2,700				
			24	2,250	2,250				
		1-3/4	11-7/8	7,560	5,200	250	675	725	615
			14	6,900	5,200				
			16	6,200	5,200				
			18	5,500	4,200				
			20	4,800	4,200				
			24	3,500	3,500				

For SI: 1 plf = 14.59 N/m, 1 lb = 4.448 N.

¹The design loads given in this table are for rim boards installed in accordance with Section 4.2.2.

²Tabulated design values are based on dry conditions of use, in which the environmental conditions (temperature and relative humidity) will result in an average equilibrium moisture content (EMC) of sawn lumber of less than 16%. Applications where the EMC will equal or exceed 16% are outside the scope of this report.

³All design values are applicable to the normal load duration (10 years) for wood products, except for the lateral load capacity, which is based on the short-term load duration (10 minutes). Design values shall be adjusted for other load durations in accordance Section 2.3.2 of the NDS except the uniform vertical load and concentrated vertical load are not allowed to be increased for any load durations shorter than the normal load duration (10 years).

⁴Other design values are as provided for 1.6E grade Pacific Woodtech LVL in Table 1.

⁵Lag screw connections between rim boards and deck ledgers have an allowable lateral load of 350 pounds per lag screw, provided the conditions in the exception to Section 4.1.2 are met

TABLE 3—EQUIVALENT SPECIFIC GRAVITY FOR CONNECTION DESIGN^{1, 2}

Connection Type – Load Direction	Fastener Orientation	
	Face ³	Edge ⁴
Nail – Withdrawal	0.50	0.47
Nail – Lateral	0.50	0.50
Bolt – Lateral	0.50	N.A.

¹Reference lateral and withdrawal design values for bolted and nailed connections in Pacific Woodtech LVL are as specified in the NDS for structural composite lumber having equivalent specific gravities as indicated in the table above. When used in wet conditions, the fastener design values shall be adjusted by the wet service factor in accordance with the NDS.

²Connections in which fasteners are installed into the end grain of the LVL are outside the scope of this report.

³Values given under the heading 'Face' apply to connections in which the fastener axis is installed perpendicular to the faces showing the wide face of one veneer.

⁴Values given under the heading 'Edge' apply to connections in which the fastener axis is installed perpendicular to the faces showing the narrow edge of all veneers.

TABLE 4—MINIMUM NAIL SPACING AND END DISTANCE¹

Nominal LVL Thickness	Orientation	Nail Size ²	Nail Diameter (in.)	Nail Length (in.)	Minimum End Distance (in.)	Minimum Nail Spacing ² (in.)		Maximum Nail Penetration ³ (in.)
						Single Row	Double Row	
Less than 1-1/2 in.	Edge	8d & smaller	0.131	2.5	2-1/2	3	NA	2.25
		10d & 12d	0.148	3.25	2-1/2	4		2.5
		16d	0.162	3.5	3-1/2	5		2
	Face ⁴	12d & smaller	0.148	3.25	1-1/2	3	3	LVL Thickness
		16d	0.162	3.5	1-1/2	5	5	LVL Thickness
1-1/2 in. and greater	Edge	8d & smaller	0.131	2.5	2-1/2	3	4	2.25
		10d & 12d	0.148	3.25	3-1/2 ⁵	4	5	2.5
		16d	0.162	3.5	3-1/2	5	6 ⁶	2
	Face ⁴	12d & smaller	0.148	3.25	1-1/2	3	3	LVL Thickness
		16d	0.162	3.5	1-1/2	5	5	LVL Thickness

For SI: 1 inch = 25.4 mm.

¹Edge distance shall be sufficient to prevent splitting.

²Nail sizes and closest on-center spacing not specifically described in this table are outside the scope of this report.

³Penetration length includes nail tip.

⁴Tabulated closest on-center spacing for face orientation is applicable to nails that are installed in rows parallel to the grain (length) of the LVL. For nails installed in rows perpendicular to the direction of grain (width/depth) of the LVL, the closest on-center spacing for face orientation shall be sufficient to prevent splitting of the LVL.

⁵Minimum end distance is allowed to be reduced to 2-1/2 in. for single row nailing.

⁶Minimum nail spacing may be reduced to 5 in. when LVL is 1-3/4 in. or thicker.

DISCLAIMER

APA Product Report[®] is a trademark of APA – *The Engineered Wood Association*, Tacoma, Washington. ICC-ES Evaluation Report is a trademark of ICC Evaluation Service, LLC (ICC-ES). The information contained herein is based on the product evaluation in accordance with the references noted in this report. Neither ICC-ES, nor APA or its members make any warranty, expressed or implied, or assume any legal liability or responsibility for the use, application of, and/or reference to opinions, findings, conclusions, or recommendations included in this report. The joint ICC-ES/APA Evaluation Reports are not to be construed as representing aesthetics or any other attributes not specifically addressed, nor are they to be construed as an endorsement of the subject of the report or a recommendation for its use. Consult the local jurisdiction or design professional to assure compliance with code, construction, and performance requirements. Because neither APA, nor ICC-ES, has any control over quality of workmanship or the conditions under which engineered wood products are used, it cannot accept responsibility for product performance or designs as actually constructed.

DIVISION: 06 00 00—WOOD, PLASTICS AND COMPOSITES

Section: 06 17 13—Laminated Veneer Lumber

REPORT HOLDER:

PACIFIC WOODTECH CORPORATION

EVALUATION SUBJECT:

PACIFIC WOODTECH® LAMINATED VENEER LUMBER (LVL), PACIFIC WOODTECH® TREATED LVL AND PACIFIC WOODTECH® RIM BOARDS

1.0 REPORT PURPOSE AND SCOPE

Purpose:

The purpose of this evaluation report supplement is to indicate that Pacific Woodtech® laminated veneer lumber (LVL), Pacific Woodtech® Treated LVL, and Pacific Woodtech® Rim Boards, described in ICC-ES evaluation report [ESR-2909](#), have also been evaluated for compliance with the codes noted below as adopted by the Los Angeles Department of Building and Safety (LADBS).

Applicable code editions:

- 2020 *City of Los Angeles Building Code* (LABC)
- 2020 *City of Los Angeles Residential Code* (LARC)

2.0 CONCLUSIONS

The Pacific Woodtech® LVL, Pacific Woodtech® Treated LVL, and Pacific Woodtech® Rim Boards described in Sections 2.0 through 7.0 of the evaluation report [ESR-2909](#), comply with the LABC Chapter 23, and the LARC, and are subjected to the conditions of use described in this supplement.

3.0 CONDITIONS OF USE

The Pacific Woodtech® LVL, Pacific Woodtech® Treated LVL, and Pacific Woodtech® Rim Boards described in this evaluation report supplement must comply with all of the following conditions:

- All applicable sections in the evaluation report [ESR-2909](#).
- The design, installation, conditions of use and identification are in accordance with the 2018 *International Building Code*® (IBC) provisions noted in the evaluation report [ESR-2909](#).
- The design, installation and inspection are in accordance with additional requirements of LABC Chapters 16 and 17, as applicable.

This supplement expires concurrently with the evaluation report, reissued September 2023.

DIVISION: 06 00 00—WOOD, PLASTICS AND COMPOSITES

Section: 06 17 13—Laminated Veneer Lumber

REPORT HOLDER:

PACIFIC WOODTECH CORPORATION

EVALUATION SUBJECT:

PACIFIC WOODTECH® LAMINATED VENEER LUMBER (LVL), PACIFIC WOODTECH® TREATED LVL AND PACIFIC WOODTECH® RIM BOARDS

1.0 REPORT PURPOSE AND SCOPE

Purpose:

The purpose of this evaluation report supplement is to indicate that Pacific Woodtech® Laminated Veneer Lumber (LVL) and Pacific Woodtech® Rim Boards, described in ICC-ES evaluation report ESR-2909, have also been evaluated for compliance with the code(s) noted below.

Applicable code editions:

- 2019 *California Building Code*® (CBC)

For evaluation of applicable chapters adopted by the California Office of Statewide Health Planning and Development (OSHPD) AKA: California Department of Health Care Access and Information (HCAI) and the Division of State Architect (DSA), see Sections 2.1.1 and 2.1.2 below.

- 2019 *California Residential Code*® (CRC)

2.0 CONCLUSIONS

2.1 CBC:

The Pacific Woodtech® Laminated Veneer Lumber (LVL) and Pacific Woodtech® Rim Boards, described in Sections 2.0 through 7.0 of the evaluation report ESR-2909, comply with CBC Chapter 23, provided the design and installation are in accordance with the 2018 *International Building Code*® (IBC) provisions noted in the evaluation report, ESR-2909, and the additional requirements of CBC Chapters 16 and 17, as applicable.

2.1.1 OSHPD:

The applicable OSHPD Sections and Chapters of the CBC are beyond the scope of this supplement.

2.1.2 DSA:

The applicable DSA Sections and Chapters of the CBC are beyond the scope of this supplement.

2.2 CRC:

The Pacific Woodtech® Laminated Veneer Lumber (LVL) and Pacific Woodtech® Rim Boards, described in Sections 2.0 through 7.0 of the evaluation report ESR-2909, comply with CRC Chapters 5 and 8, provided the design and installation are in accordance with the 2018 *International Residential Code*® (IRC) provisions noted in the evaluation report ESR-2909.

This supplement expires concurrently with the evaluation report, reissued September 2023.

DIVISION: 06 00 00—WOOD, PLASTICS AND COMPOSITES
Section: 06 17 13—Laminated Veneer Lumber

REPORT HOLDER:

PACIFIC WOODTECH CORPORATION

EVALUATION SUBJECT:

PACIFIC WOODTECH® LAMINATED VENEER LUMBER (LVL), PACIFIC WOODTECH® TREATED LVL AND PACIFIC WOODTECH® RIM BOARDS

1.0 REPORT PURPOSE AND SCOPE**Purpose:**

The purpose of this evaluation report supplement is to indicate that Pacific Woodtech® laminated veneer lumber (LVL), Pacific Woodtech® Treated LVL, and Pacific Woodtech® Rim Boards, described in ICC-ES evaluation report ESR-2909, have also been evaluated for compliance with the codes noted below.

Applicable code editions:

- 2020 *Florida Building Code—Building*
- 2020 *Florida Building Code—Residential*

2.0 CONCLUSIONS

The Pacific Woodtech® LVL, Pacific Woodtech® Treated LVL, and Pacific Woodtech® Rim Boards, described in Sections 2.0 through 7.0 of the evaluation report ESR-2909, comply with the *Florida Building Code—Building* and the *Florida Building Code—Residential*, provided the design requirements are determined in accordance with the *Florida Building Code—Building* or the *Florida Building Code—Residential*, as applicable. The installation requirements noted in evaluation report ESR-2909 for the 2018 *International Building Code*® meet the requirements of the *Florida Building Code—Building* or the *Florida Building Code—Residential*, as applicable.

Use of the Pacific Woodtech® LVL, Pacific Woodtech® Treated LVL, and Pacific Woodtech® Rim Boards for compliance with the High-Velocity Hurricane Zone provisions of the *Florida Building Code—Building* and the *Florida Building Code—Residential* has not been evaluated, and is outside the scope of this evaluation report supplement.

For products falling under Florida Rule 61G20-3, verification that the report holder's quality assurance program is audited by a quality assurance entity approved by the Florida Building Commission for the type of inspections being conducted is the responsibility of an approved validation entity (or the code official when the report holder does not possess an approval by the Commission).

This supplement expires concurrently with the evaluation report, reissued September 2023.